

# EUROPEAN PATENT OFFICE

## Patent Abstracts of Japan

PUBLICATION NUMBER : 05070910  
PUBLICATION DATE : 23-03-93

APPLICATION DATE : 01-04-91  
APPLICATION NUMBER : 03092632

APPLICANT : SUMITOMO LIGHT METAL IND LTD;

INVENTOR : YOSHIDA HIDEO;

INT.CL. : C22F 1/053 C22C 21/10

TITLE : PRODUCTION OF SOFT ALUMINUM ALLOY MATERIAL FOR WELDED STRUCTURE

ABSTRACT : PURPOSE: To produce a soft Al-Zn-Mg alloy material for a welded structure having excellent cold workability.

CONSTITUTION: An Al alloy contg. 3-8% Zn, 0.5-3.0% Mg, 0.01-0.5% Cu and one or more among 0.005-0.30% Ti, 0.05-0.7% Mn, 0.01-0.5% Cr, 0.05-0.30% Zr and 0.01-0.15% V is hot worked, held under heating at 180-320°C for 0.5-24hr and cooled to room temp. to obtain an Al-Zn-Mg alloy for a welded structure having excellent cold workability and hardly undergoing a change with the lapse of time due to aging at room temp.

COPYRIGHT: (C)1993,JPO&Japio

**\* NOTICES \***

JPO and INPIT are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. \*\*\*\* shows the word which can not be translated.
3. In the drawings, any words are not translated.

---

**CLAIMS**

---

[Claim(s)]

[Claim 1] Zn: 3-8% (it is the same weight criteria and the following), Mg:0.5-3.0%, Cu:0.01-0.5% is contained. And Ti:0.005-0.30%, Mn: 0.05-0.7%, Cr:0.01-0.5%, Zr:0.05-0.30%, aluminum alloy which consists of the remainder aluminum and an impurity or more including one of V:0.01 - 0.15% of sorts The manufacture approach of the welding structural steel worker aluminum alloy elasticity material characterized by cooling to an after [ 0.5 - 24 hour heating maintenance ] room temperature at the temperature of 180-320 degrees C as softening processing after hot working using the usual production process.

---

[Translation done.]

**\* NOTICES \***

JPO and INPIT are not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. \*\*\*\* shows the word which can not be translated.
3. In the drawings, any words are not translated.

---

**DETAILED DESCRIPTION**

---

**[Detailed Description of the Invention]**

[0001]

[Industrial Application] This invention relates to the manufacture approach of the welding structural steel worker aluminum-Zn-Mg system alloy elasticity material excellent in cold-working nature.

[0002]

[Description of the Prior Art] The approach of there being JIS-7N01 alloy, and the annealing conditions of this alloy carrying out furnace cooling after heating to 415 degrees C, or cooling them in after [ 2 hour heating maintenance ] air at 410-430 degrees C, reheating at about 330 degrees C, and holding to this temperature as a typical welding structural steel worker aluminum-Zn-Mg alloy, for about 4 hours, and cooling to a room temperature is recommended.

[0003]

[Problem(s) to be Solved by the Invention] However, by a solute component's forming cooling conditions also as furnace cooling, and leaving a supersaturated solid solution in the room temperature after cooling, an age-hardening arises and the former reduces the cold-working nature of elasticity material. Moreover, complicatedness is accompanied by the latter in order to have to perform heat treatment twice. This invention improves these points.

[0004]

[Means for Solving the Problem] This invention contains Zn:3-8%, Mg:0.5-3.0%, and Cu:0.01-0.5%. And Ti:0.005-0.30%, Mn:0.05-0.7%, One or more of Cr:0.01-0.5%, Zr:0.05-0.30%, and V:0.01 - 0.15% of sorts are included. It is the manufacture approach of the welding structural steel worker aluminum alloy elasticity material characterized by cooling aluminum alloy which consists of the remainder aluminum and an impurity to an after [ 0.5 - 24 hour heating maintenance ] room temperature at the temperature of 180-320 degrees C as softening processing after hot working using the usual production process.

[0005] By setting the softening processing after hot working as the above-mentioned range, by depositing an alloy content by one heat treatment, and reducing the amount of dissolution in a host phase, and making the deposit particle make it condensation big and rough, the deformation resistance between the colds is reduced and the age-hardening at the time of room temperature neglect is controlled in this invention.

[0006] The reason for definition of an alloy presentation is as follows.

Zn: Raise the reinforcement in a room temperature. When reinforcement high at T four or T6 material is not obtained at less than 3% but 8% is exceeded, stress corrosion cracking is made easy to generate.

Mg: Raise the reinforcement in a room temperature. At less than 0.5%, if high reinforcement is not obtained by T four or T6 material but 3% is exceeded, hot-working nature will be degraded and it will become easy to generate stress corrosion cracking.

[0007] Cu: Improve stress-corrosion-cracking nature. At less than 0.01%, even if there is little effectiveness and it exceeds 0.5%, the improvement effect is saturated and degrades weldability.

Ti: Effectiveness is in detailed-izing of cast structure, and prevention of the ingot crack at the time of casting. At less than 0.005%, if it is ineffective and 0.30% is exceeded, a huge intermetallic compound crystallizes and is not desirable.

Mn, Cr, Zr, V: These elements have effectiveness in grain refining. Big and rough-ization of crystal grain starts dry rough skin at the time of cold working of bending etc. Moreover, stress-corrosion-cracking-proof nature is improved. It forms a huge crystallization object at the time of DC casting generally used industrially and is not desirable, if there is little this effectiveness and it adds exceeding this, when adding under each lower limit.

[0008] Moreover, an impurity means Fe and Si in this case. The ingredient applied to softening processing of this invention is limited to an ingredient with hot working, such as hot rolling material and hot extrusion material. It is because, as for a reason, it is needed seen from a metal texture that elasticity material is in the condition of recovery or recrystallization and the ingredient of a hot-working riser has this organization.

[0009] Softening processing of this invention aims the dissolution component in a host phase (mainly Zn, Mg) the

shape of a particle at a deposit, condensation, and making it make it big and rough. A host phase is dissolution--ization--strengthened by the dissolution component as a deposit is inadequate, and the deformation resistance under cold working goes up. Moreover, when long-term storage is carried out in a room temperature, for example as an inventory, by aging deposit, proof stress and tensile strength rise and elongation falls. Furthermore, a deposit particle must be adjusted in the range of 0.01-10 micrometers by condensation and big and rough-ization in order to make deformation resistance small. For this reason, the heating maintenance conditions at the time of softening processing must be set to 0.5-24h at the temperature of 180-320 degrees C. At less than 180 degrees C, if prolonged maintenance is not performed, a dissolution component cannot be deposited enough, and there is no merit economically. When the tensile strength immediately after softening is left in the room temperature after cooling even if it is low since it becomes inadequate the dissolution component which was supersaturated depositing even if it causes re-dissolution of an alloy content and cools byh in 30 degrees C /or less from this temperature when 320 degrees C is exceeded, since an age-hardening arises, tensile strength rises. the case where the holding time is less than 0.5h -- an alloy content -- a deposit - - and it cannot be made to make it condensation big and rough Moreover, holding exceeding 24h causes too much grain boundary deposit economically there are not only few merits, but, and ductility falls.

[0010] A field exceeds 250 degrees C whenever [ stoving temperature ], and h of a cooling rate is desirable in 30 degrees C /the case to 320 degrees C. If the part equivalent to the difference of the solid-solution limit of the alloy element in this temperature field and the solid-solution limit in a temperature field 250 degrees C or less has a quick cooling rate, it will be that it is supersaturated and will form the solid solution. This has a possibility of causing the age-hardening in a room temperature. Since a supersaturated part can be enough deposited if it cools to a temperature field 250 degrees C or less byh in 30 degrees C /or less, it does not become a problem. Moreover, if it is from the heating retention temperature of 250 degrees C or less, it will not be based on a cooling rate and the age-hardening in a room temperature will not become a problem.

[0011]

[Example] Ingot making of the alloy shown in a table 1 was carried out to 30mm(thickness) x200mm(width) x200mm (merit), and homogenization of 460 degree-Cx12h was performed. It hot-rolled from 450 degrees C, and this ingot was used as the plate with a thickness of 2mm. Annealing was performed using the conditions which showed this hot rolling plate in a table 2, and various kinds of assessment was performed.

[0012] In a table 3, it is judging by considering that whose elongation the mechanical property immediately after softening processing is 250 or less MPa of tensile strength as a rule of thumb of cold-working nature, and is 20% or more as acceptance (O). Moreover, in order to investigate how a mechanical property changes with room temperature aging at the time of storage, the mechanical property of the ingredient left after softening processing on the 90th was investigated. What did not go up by 15 or more MPas as compared with the tensile strength immediately after softening was judged as acceptance (O). The reinforcement of Ushiro who processed the softened ingredient T6 was investigated supposing being used for the part for which reinforcement is needed as a welding structural steel worker. After holding 460 degree-Cx1h of T6 conditions, water cooling of them was carried out, and they performed annealing of 120 degree-Cx24h. It judged by considering having 350 or more MPas as acceptance (O) with tensile strength. Next, testing of stress corrosion cracking of T6 material was performed. Mutual immersion was performed for 30 days into 3.5% of NaCl water solution, using and carrying out the 196MPa load of the 1 No. B test piece to JISH8711 one by one. What the crack after test termination for 30 days did not generate was considered as acceptance (O).

[0013]

[A table 1]

| 合 金              | Z n | M g | C u | T i  | M n  | C r  | Z r  | V         |
|------------------|-----|-----|-----|------|------|------|------|-----------|
| 本<br>発<br>明<br>例 | A   | 4.0 | 2.0 | 0.15 | 0.02 | —    | —    | —         |
|                  | B   | 4.1 | 2.1 | 0.17 | —    | 0.35 | —    | —         |
|                  | C   | 4.4 | 2.0 | 0.18 | —    | —    | 0.15 | —         |
|                  | D   | 4.2 | 2.3 | 0.20 | —    | —    | 0.18 | —         |
|                  | E   | 4.5 | 2.0 | 0.17 | —    | —    | —    | 0.07      |
|                  | F   | 6.2 | 2.0 | 0.14 | 0.02 | 0.10 | 0.12 | —         |
|                  | G   | 6.4 | 2.1 | 0.16 | 0.02 | —    | —    | 0.15 0.05 |
| 比<br>較<br>例      | H   | 9.5 | 2.0 | 0.15 | 0.02 | —    | —    | 0.18 —    |
|                  | I   | 2.2 | 2.0 | 0.15 | 0.02 | —    | —    | 0.17 —    |
|                  | J   | 4.5 | 0.2 | 0.16 | 0.02 | —    | —    | 0.17 —    |
|                  | K   | 4.2 | 2.2 | —    | 0.02 | —    | —    | 0.18 —    |
|                  | L   | 4.0 | 2.1 | 0.16 | —    | —    | —    | —         |

Notes: wt%, \*\* aluminum, and an impurity [0014]  
[A table 2]

|             | 条 件    |          |
|-------------|--------|----------|
|             | 温度 (℃) | 保持時間 (h) |
| 1 (本発明例)    | 2 1 0  | 1 2      |
| 2 (   "   ) | 2 8 0  | 6        |
| 3 (   "   ) | 3 2 0  | 2        |
| 4 (比較例)     | 1 5 0  | 2 4      |
| 5 (   "   ) | 3 5 0  | 1        |

[0015]  
[A table 3]

|      | 合金 | 熱処理 | 軟化直後        |           |    | 軟化後90日室温放置  |                        |    | T6処理後       |    | 応力腐食割れ試験 |
|------|----|-----|-------------|-----------|----|-------------|------------------------|----|-------------|----|----------|
|      |    |     | 引張強さ<br>MPa | 伸び<br>(%) | 判定 | 引張強さ<br>MPa | 軟化直後の<br>引張強さとの差 (MPa) | 判定 | 引張強さ<br>MPa | 判定 |          |
| 本発明例 | A  | 1   | 233         | 24        | ○  | 238         | 5                      | ○  | 370         | ○  | ○        |
|      | B  | 1   | 239         | 25        | ○  | 239         | 0                      | ○  | 375         | ○  | ○        |
|      | C  | 2   | 221         | 25        | ○  | 223         | 2                      | ○  | 372         | ○  | ○        |
|      | D  | 2   | 213         | 25        | ○  | 220         | 7                      | ○  | 368         | ○  | ○        |
|      | E  | 2   | 220         | 25        | ○  | 232         | 12                     | ○  | 372         | ○  | ○        |
|      | F  | 3   | 240         | 26        | ○  | 246         | 6                      | ○  | 392         | ○  | ○        |
|      | G  | 3   | 244         | 23        | ○  | 250         | 6                      | ○  | 398         | ○  | ○        |

|      |   |   |     |    |   |     |    |   |     |   |   |
|------|---|---|-----|----|---|-----|----|---|-----|---|---|
| 本発明例 | H | 2 | 249 | 23 | ○ | 258 | 9  | ○ | 405 | ○ | × |
|      | I | 2 | 195 | 28 | ○ | 203 | 8  | ○ | 312 | × | ○ |
|      | J | 2 | 180 | 30 | ○ | 183 | 3  | ○ | 280 | × | ○ |
|      | K | 2 | 210 | 26 | ○ | 217 | 7  | ○ | 355 | ○ | × |
|      | L | 2 | 225 | 25 | ○ | 226 | 1  | ○ | 370 | ○ | × |
|      | A | 4 | 322 | 17 | × | 325 | 3  | ○ | 368 | ○ | ○ |
|      | D | 5 | 218 | 25 | ○ | 252 | 34 | × | 372 | ○ | ○ |
|      | H | 5 | 243 | 24 | ○ | 290 | 47 | × | 415 | ○ | × |

[0016]

[Effect of the Invention] According to this invention, the welding structural steel worker alloy which the deformation resistance between the colds was reduced and controlled the age-hardening at the time of room temperature neglect by one heat treatment can be manufactured.

[Translation done.]

(19)日本国特許庁(JP)

(12)公開特許公報(A)

(11)特許出願公開番号

特開平5-70910

(43)公開日 平成5年(1993)3月23日

| (51)Int.Cl. <sup>5</sup> | 識別記号 | 庁内整理番号  | FI | 技術表示箇所 |
|--------------------------|------|---------|----|--------|
| C 2 2 F 1/053            |      | 9157-4K |    |        |
| C 2 2 C 21/10            |      | 8928-4K |    |        |

審査請求 未請求 請求項の数1(全 5 頁)

(21)出願番号 特願平3-92632

(22)出願日 平成3年(1991)4月1日

(71)出願人 000002277

住友軽金属工業株式会社  
東京都港区新橋5丁目11番3号

(72)発明者 松田 真一

愛知県名古屋市港区千年3丁目1番12号  
住友軽金属工業株式会社技術研究所内

(72)発明者 吉田 英雄

愛知県名古屋市港区千年3丁目1番12号  
住友軽金属工業株式会社技術研究所内

(74)代理人 弁理士 小松 秀岳 (外2名)

(54)【発明の名称】 溶接構造用アルミニウム合金軟質材の製造方法

(57)【要約】

【目的】 冷間加工性に優れた溶接構造用Al-Zn-Mg合金軟質材を製造する。

【構成】 Zn:3~8%、Mg:0.5~3.0%、Cu:0.01~0.5%、さらにTi:0.005~0.30%、Mn:0.05~0.7%、Cr:0.01~0.5%、Zr:0.05~0.30%、V:0.01~0.15%のうち1種以上含むAl合金を熱間加工後、180~320℃で0.5~24h加熱保持後室温まで冷却する方法である。

【効果】 室温時効による経時変化の少ない冷間加工性に優れた溶接構造用Al-Zn-Mg合金が得られる。

## 【特許請求の範囲】

【請求項1】 Zn: 3~8% (重量基準、以下同じ)、Mg: 0.5~3.0%、Cu: 0.01~0.5%を含有し、かつ、Ti: 0.005~0.30%、Mn: 0.05~0.7%、Cr: 0.01~0.5%、Zr: 0.05~0.30%、V: 0.01~0.15%のうち1種以上を含み、残部Al及び不純物からなるAl合金を、通常の製造工程を用いて熱間加工後、軟化処理として180~320℃の温度で0.5~24時間加熱保持後室温まで冷却することを特徴とする溶接構造用アルミニウム合金軟質材の製造方法。

## 【発明の詳細な説明】

## 【0001】

【産業上の利用分野】 本発明は、冷間加工性に優れた溶接構造用Al-Zn-Mg系合金軟質材の製造方法に関する。

## 【0002】

【従来の技術】 代表的な溶接構造用Al-Zn-Mg合金として、JIS-7N01合金があり、この合金の焼き鈍し条件は415℃まで加熱後炉冷をするか、又は410~430℃で2時間加熱保持後空气中で冷却し、約330℃に再加熱し、この温度に約4時間保持し、それから室温まで冷却する方法が推奨されている。

## 【0003】

【発明が解決しようとする課題】 しかし、前者は冷却条件を炉冷としても、溶質成分が過飽和固溶体を形成し、冷却後室温に放置することにより時効硬化が生じて軟質材の冷間加工性を低下させる。又、後者は2回熱処理を行わなければならないため、煩雑さが伴う。本発明はこれらの点を改善するものである。

## 【0004】

【課題を解決するための手段】 本発明は、Zn: 3~8%、Mg: 0.5~3.0%、Cu: 0.01~0.5%を含有し、かつ、Ti: 0.005~0.30%、Mn: 0.05~0.7%、Cr: 0.01~0.5%、Zr: 0.05~0.30%、V: 0.01~0.15%のうち1種以上を含み、残部Al及び不純物からなるAl合金を、通常の製造工程を用いて熱間加工後、軟化処理として180~320℃の温度で0.5~24時間加熱保持後室温まで冷却することを特徴とする溶接構造用アルミニウム合金軟質材の製造方法である。

【0005】 本発明では、熱間加工後の軟化処理を上記範囲に設定することにより、1回の熱処理で合金成分を析出させて母相中の固溶量を低減して、かつ、その析出粒子を凝集粗大化させることにより冷間における変形抵抗を低下させ、かつ、室温放置時の時効硬化を抑制する。

## 【0006】 合金組成の限定理由は次の通りである。

Zn: 室温における強度を上昇させる。3%未満ではT4あるいはT6材で高い強度が得られず、8%を越える

と応力腐食割れを発生しやすくなる。

Mg: 室温における強度を上昇させる。0.5%未満ではT4あるいはT6材で高い強度が得られず、3%を越えると熱間加工性を劣化させ、また、応力腐食割れを発生しやすくなる。

【0007】 Cu: 応力腐食割れ性を改善する。0.01%未満では効果が少なく、0.5%を越えてもその改善効果は飽和し、又、溶接性を劣化させる。

Ti: 铸造組織の微細化および铸造時の铸造割れの防止に効果がある。0.005%未満では効果がなく、0.30%を越えると巨大な金属間化合物が晶出し好ましくない。

Mn, Cr, Zr, V: これらの元素は、結晶粒微細化に効果がある。結晶粒の粗大化は曲げ加工などの冷間加工時に肌あれを起す。又、耐応力腐食割れ性を改善する。それぞれの下限値未満しか添加しない場合はこの効果が少なく、これを越えて添加すると、一般に工業的に用いられるDC铸造時に巨大な晶出物を形成し好ましくない。

【0008】 又、不純物とはこの場合Fe, Siを意味する。本発明の軟化処理に適用される材料は、熱間圧延材、熱間押出材などの熱間加工のままの材料に限定される。理由は、金属組織からみて軟質材は回復あるいは再結晶の状態であることが必要とされ、熱間加工上がりの材料はこの組織を有しているからである。

【0009】 本発明の軟化処理は、母相中の固溶成分（主にZn, Mg）を粒子状に析出、凝集、粗大化させることを目的としている。析出が不十分であると、固溶成分によって母相が固溶強化され、冷間加工中の変形抵抗が上昇する。又、例えば在庫として室温において長期保管された場合に、時効析出によって耐力および引張強さが上昇し、伸びが低下する。さらに析出粒子は、変形抵抗を小さくするため、凝集・粗大化によって0.01~10μmの範囲に調整されなければならない。このため、軟化処理時の加熱保持条件は180~320℃の温度で0.5~24hとしなければならない。180℃未満では、長時間保持を行わなければ固溶成分を十分析出させることができず、経済的にメリットがない。320℃を越えた場合、合金成分の再固溶を招き、この温度から30℃/h以下で冷却を行っても過飽和となった固溶成分の析出が不十分となるため、軟化直後の引張強さは低くても、冷却後室温に放置した場合に、時効硬化が生じるため引張強さは上昇する。保持時間が0.5h未満の場合、合金成分を析出および凝集粗大化させることができない。又、24hを越えて保持することは経済的にメリットが少ないばかりでなく、過度の粒界析出を招いて延性が低下する。

【0010】 加熱温度領域が250℃を越え320℃までの場合、冷却速度は30℃/hが望ましい。この温度領域での合金元素の固溶限と250℃以下の温度領域に



おける固溶限との差に相当する分が、冷却速度が速いと過飽和となって固溶体を形成する。これは、室温における時効硬化を招く恐れがある。30℃/h以下で250℃以下の温度領域まで冷却すれば過飽和分を十分析出させることができるため問題とはならない。又、250℃以下の加熱保持温度からであれば、冷却速度によらず、室温での時効硬化は問題にならない。

## 【0011】

【実施例】表1に示す合金を30mm(厚)×200mm(巾)×200mm(長)に造塊し、460℃×12hの均質化処理を行った。この铸塊を450℃より熱間圧延を行って厚さ2mmの板とした。この熱間圧延板を表2に示した条件を用いて焼鈍を行って各種の評価を行った。

【0012】表3中で、冷間加工性の目安として軟化処理直後の機械的性質が引張強さ250MPa以下で、かつ伸びが20%以上であるものを合格(O)として判定\*

\*を行っている。又、保管時に室温時効によって機械的性質がどの様に変化するかを調査するため、軟化処理後90日放置した材料の機械的性質を調査した。軟化直後の引張強さと比較して15MPa以上上昇しなかったものを合格(O)として判定した。溶接構造用として強度を必要とされる部位に使用されることを想定し、軟化した材料をT6処理した後の強度を調査した。T6条件は460℃×1h保持した後水冷し、120℃×24hの焼戻しを行った。引張強さで350MPa以上を有していることを合格(O)として判定を行った。次にT6材の応力腐食割れ試験を行った。JISH8711に順次1B号試験片を用いて196MPa負荷したまま、3.5%のNaCl水溶液中に30日間交互浸漬を行った。30日間の試験終了後割れの発生しなかったものを合格(O)とした。

## 【0013】

## 【表1】

| 合 金              | Zn | Mg  | Cu  | Ti   | Mn   | Cr   | Zr   | V    |
|------------------|----|-----|-----|------|------|------|------|------|
| 本<br>発<br>明<br>例 | A  | 4.0 | 2.0 | 0.15 | 0.02 | —    | —    | —    |
|                  | B  | 4.1 | 2.1 | 0.17 | —    | 0.35 | —    | —    |
|                  | C  | 4.4 | 2.0 | 0.18 | —    | —    | 0.15 | —    |
|                  | D  | 4.2 | 2.3 | 0.20 | —    | —    | 0.18 | —    |
|                  | E  | 4.5 | 2.0 | 0.17 | —    | —    | —    | 0.07 |
|                  | F  | 6.2 | 2.0 | 0.14 | 0.02 | 0.10 | 0.12 | —    |
|                  | G  | 6.4 | 2.1 | 0.16 | 0.02 | —    | 0.15 | 0.05 |
| 比<br>較<br>例      | H  | 9.5 | 2.0 | 0.15 | 0.02 | —    | 0.18 | —    |
|                  | I  | 2.2 | 2.0 | 0.15 | 0.02 | —    | 0.17 | —    |
|                  | J  | 4.5 | 0.2 | 0.16 | 0.02 | —    | 0.17 | —    |
|                  | K  | 4.2 | 2.2 | —    | 0.02 | —    | 0.18 | —    |
|                  | L  | 4.0 | 2.1 | 0.16 | —    | —    | —    | —    |

注：wt%、類A1及び不純物

## 【0014】

## 【表2】

\*【表3】

|          | 条 件     |          |
|----------|---------|----------|
|          | 温度 (°C) | 保持時間 (h) |
| 1 (本発明例) | 210     | 12       |
| 2 ( 〃 )  | 280     | 6        |
| 3 ( 〃 )  | 320     | 2        |
| 4 (比較例)  | 150     | 24       |
| 5 ( 〃 )  | 350     | 1        |

【0015】

\*

|                  | 合<br>金 | 熱<br>処<br>理 | 軟化直後            |           |        | 軟化後90日室温放置      |                            |        | T6処理後           |        | 応力腐<br>食割れ<br>試験 |
|------------------|--------|-------------|-----------------|-----------|--------|-----------------|----------------------------|--------|-----------------|--------|------------------|
|                  |        |             | 引張<br>強さ<br>MPa | 伸び<br>(%) | 判<br>定 | 引張<br>強さ<br>MPa | 軟化直後の<br>引張強さとの<br>差 (MPa) | 判<br>定 | 引張<br>強さ<br>MPa | 判<br>定 |                  |
| 本<br>発<br>明<br>例 | A      | 1           | 233             | 24        | ○      | 238             | 5                          | ○      | 370             | ○      | ○                |
|                  | B      | 1           | 239             | 25        | ○      | 239             | 0                          | ○      | 375             | ○      | ○                |
|                  | C      | 2           | 221             | 25        | ○      | 223             | 2                          | ○      | 372             | ○      | ○                |
|                  | D      | 2           | 213             | 25        | ○      | 220             | 7                          | ○      | 368             | ○      | ○                |
|                  | E      | 2           | 220             | 25        | ○      | 232             | 12                         | ○      | 372             | ○      | ○                |
|                  | F      | 3           | 240             | 26        | ○      | 246             | 6                          | ○      | 392             | ○      | ○                |
|                  | G      | 3           | 244             | 23        | ○      | 250             | 6                          | ○      | 398             | ○      | ○                |

| 7                |   |   |     |    |   |     | 8   |   |     |   |   |
|------------------|---|---|-----|----|---|-----|-----|---|-----|---|---|
| 本<br>発<br>明<br>例 | H | 2 | 249 | 23 | ○ | 258 | 9   | ○ | 405 | ○ | × |
|                  | I | 2 | 195 | 28 | ○ | 203 | 8   | ○ | 312 | × | ○ |
|                  | J | 2 | 180 | 30 | ○ | 183 | 3   | ○ | 280 | × | ○ |
|                  | K | 2 | 210 | 26 | ○ | 217 | 7   | ○ | 355 | ○ | × |
|                  | L | 2 | 225 | 25 | ○ | 226 | 1   | ○ | 370 | ○ | × |
|                  | A | 4 | 322 | 17 | × | 325 | 3   | ○ | 368 | ○ | ○ |
|                  | D | 5 | 218 | 25 | ○ | 252 | 3 4 | × | 372 | ○ | ○ |
|                  | H | 5 | 243 | 24 | ○ | 290 | 4 7 | × | 415 | ○ | × |

【0016】

【発明の効果】本発明によれば、1回の熱処理で、冷間

における変形抵抗を低下させ、かつ室温放置時の時効硬化を抑制した溶接構造用合金を製造することができる。